

# VINYL WASH PRIMER

Product Data Sheet (Revised 24/11/21)

## **PRODUCT CATEGORY**

Industrial – High Performance Coatings

## **PRODUCT CODE**

50-1619 Vinyl Wash Primer Pt.A  
50-1620 Vinyl Wash Primer Pt.B

## **DESCRIPTION**

A two-part chemical and corrosion resistant primer for aluminum and galvanized steel surfaces. It is a reactive primer that etches the surface to help promote adhesion.

## **RECOMMENDED USE**

Suitable for interim protection of galvanized or aluminum tanks, pipes and marine applications. It's main function is to provide good adhesion for subsequent topcoats.

## **FEATURES AND BENEFITS**

Quick dry time, fast recoat, flat finish, durable finish, water submersible, chemical resistant, abrasion resistant. Easy to use 1:1 mix ratio.

## **PACKAGING**

2 x 3.7 L bottle, 2-part system

## **TINT AND BASE INFORMATION**

Clear

## **PRODUCT DATA**

**Mix Ratio:** 1 part of Part A : 1 part of Part B ( By volume )

Data below based on potted mix.

**Gloss:** Satin

**VOC:** 765 g/l

**Coverage:** Approx. 150 sqft / gal at 1mil DFT (mixed gallon) **DFT:** 1 mil to 2 mils wet recommended

**Weight-Volume:** Approximately .88 kg/ litre

**Weight-Solids:** Approximately 15% solids by weight

### **DISCLAIMER**

The technical data furnished above by the Consolidated Coatings Company is provided for information purposes only and is, to the best of our knowledge. Since application methods and conditions are beyond our control, we cannot offer a guarantee or warranty, representation, or condition, express or implied, whether arising by statute, by operation of law, or otherwise, (including merchantability or fitness for a particular purpose) with respect to this product and we assume no responsibility or liability of any kind for coverage, performance or damage (whether arising from negligence of the vendor or otherwise) resulting from the installation, operation, use or performance of this product.

## **MIXING & APPLICATION INFORMATION**

Mix thoroughly, component A with component B on a 1:1 ratio, let stand for 10 minutes and remix before and during use. Pot life is approximately 8 hours. Air or airless spray application is recommended. (Airless: 3000 psi with 0.013"- 0.017" tip) (Brush: Natural Bristle Brush) (Roller: 9-10mm nap, solvent resistant core) Thinning is not required for most applications.

## **GENERAL SURFACE PREPARATION**

The surface to be coated must be dry, clean and free of oil, grease, release agents and foreign material. SSPC SP6 cleaning or better is required, for use on metal surfaces for non-immersion. On aluminum surfaces, prepare surface using SSPC-SP1, brush blast and remove contaminants before applying the vinyl wash primer.

## **SAFETY**

Proper safety procedures should be followed at all times while handling this product. In confined areas, personal protection equipment and explosion proof application equipment should be used. Keep containers away from heat, flame or sparks when not in use. Use with adequate ventilation. Keep from the reach of children. Read all label directions and Safety Data Sheet for health and safety information prior to use.

## **DRYING TIME**

@ 25°C: To touch: 30 minutes, Recoat: 2 hours

## **CLEAN-UP**

Clean with thinners



7651 Vantage Way, Delta, BC, Canada, V4G 1A6

T: 604-946-7626 | F: 604-946-9609 | TF: 1-800-663-5690