

# **HIGH SOLIDS PRIMER - GREY**

Product Data Sheet (Revised 24/11/21)

### PRODUCT CATEGORY

Industrial - Coatings

### **PRODUCT CODE**

50-6053

#### DESCRIPTION

A high solids alkyd grey primer for interior and exterior surfaces. Low odor, VOC compliant.

# **RECOMMENDED USE**

For shop application on interior and exterior structural steel, beams and posts. Corrosion resistant under normal atmospheric conditions. May be coated with alkyd and water based top coats.

### **FEATURES AND BENEFITS**

Low VOC, easy application and clean-up, low odor, greater worker safety to traditional solvent based systems.

### **PACKAGING**

18.9 L Pail, 205 L Drums, 1000 L Totes

### **TINT AND BASE INFORMATION**

Clear and custom colors

# PRODUCT DATA

Gloss: Flat - Low Gloss

VOC: 340 g/l

Coverage: Approx. 448 sq.ft ./ US gal. 11.2S q. M.L.

DFT: 2 mil or greater recommended

Weight-Volume: Approximately 1.46kg/litre

**Volume-Solids:** Approximately 56% solids by volume **Weight-Solids:** Approximately 77% solids by weight

Drying Time: (@ 25°C) Tack Free Dry: 30 min., Hard Dry: 5 hours

Clean up: Clean up with 85-0311 (Xylene).

### DISCLAIMER

The technical data furnished above by the Consolidated Coatings Company is provided for information purposes only and is, to the best of our knowledge. Since application methods and conditions are beyond our control, we cannot offer a guarantee or warranty, representation, or condition, express or implied, whether arising by statute, by operation of law, or otherwise, (including merchantability or fitness for a particular purpose) with respect to this product and we assume no responsibility iniability of any kind for coverage, performance or damage (whether arising from negligence of the vendor or otherwise) resulting from the installation, operation, use or performance of this product.

### **MIXING & APPLICATION INFORMATION**

Thinners required: 85-0303 (Mineral Spirits). Not usually required. This product is mainly applied by spraying. Film Thickness: 2.0 to 3.0 mils dry mils.

### **SAFETY**

Proper safety procedures should be followed at all times while handling this product. In confined areas, personal protection equipment should be used.

### **GENERAL SURFACE PREPARATION**

The surface should be above 7° C and free of dirt, oil or grease.

### **LIMITATIONS OF USE**

Apply only when ambient and surface temperatures are above 10 degrees Celsius.

### **CLEAN UP**

Clean up with C.C.C 85-0311 (Xylene).

## DISPOSAL

Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

