

ACRYLIC URETHANE GLOSS

Product Data Sheet (Revised 24/11/21)

PRODUCT CATEGORY

High Performance Coatings – Industrial (Heavy Duty)

PRODUCT CODE

52-2000

DESCRIPTION

A high build, high performance, two component aliphatic urethane.

RECOMMENDED USE

For use on properly prepared steel, galvanized, aluminum and concrete floors. For use on exterior or interior structural steel, piping, metal buildings, conveyors, pumps, storage tank exteriors, motors, machinery and transportation vehicles.

FEATURES AND BENEFITS

Quick dry time, fast recoat, high gloss finish, hard durable finish, excellent abrasion resistant, chemical resistant, tintable, low VOC, high build application, suitable for direct to metal application.

PACKAGING

3.7 L Can, 18.9 L Pail

TINT AND BASE INFORMATION

White, Black and Clear and Tinted Base to a variety of colors

PRODUCT DATA

Mix Ratio: 4 parts of Part A : 1 part of Part B (By volume) Data below based on potted mix.

Gloss: Gloss, 85 or above at 60°

VOC: 340 g/l

Coverage: Theoretical: Approx. 960 sqft / gal at 1mil DFT

DFT: 4 mil to 6 mil recommended

Weight-Volume: Approximately 1.24 kg/ litre

Volume-Solids: Approximately 60% solids by volume

Weight-Solids: Approximately 72% solids by weight

Drying Time: Dust free: 30 minutes, (@ 25°C) ,

Recoat: 3 hours, Hard Dry: 5 hours

Clean up: Clean with thinners (85-0337)

MIXING & APPLICATION INFORMATION

Mix 4 parts of "A" with a power agitator and add 1 part of "B" curing agent and mix thoroughly before and during use. Pot life: Approx. 8 hours at 25°C. Air or airless spray application is recommended. (Conventional Air: 0.07" fluid tip is recommended) (Airless:3000 psi with 0.015"- 0.019" tip) (Brush: Natural Bristle Brush) (Roller: Limited use, 9-10mm nap, solvent resistant core) Thinning is not required for most applications. If desired, a small amount of 85-0337 solvent can be used if desired and permitted by local VOC regulations.

SAFETY

Proper safety procedures should be followed at all times while handling this product. In confined areas, personal protection equipment and explosion proof application equipment should be used. Keep containers away from heat, flame or sparks when not in use. Use with adequate ventilation. Keep from the reach of children. Read all label directions and Safety Data Sheet for health and safety information prior to use.

GENERAL SURFACE PREPARATION

The surface to be coated must be dry, clean and free of oil, grease, release agents curing compounds and foreign material. Remove all rust mill scale and loose paint before application. Steel: Use abrasive blast to minimum SSPC-SP6. For best appearance, the primer or undercoat should be smooth and free of any surface defects. Prime using a phenolic (50-6017) or epoxy based primer (60-1013). For galvanized steel: Remove dirt and oil by using a solvent cleaner and rinse. Prime with a suitable primer before applying urethane coating. For direct to metal use, blast with abrasive to SSPC-SP7 and prime with a suitable primer. For concrete: Let concrete cure for at least 30 days, use acid etch or use abrasive blast. Prime with epoxy primer. (60-1013).

LIMITATIONS OF USE

Apply only when ambient and surface temperatures are above 5 degrees Celsius. For professional use only. Immediately after use place rags, steel wool and waste soaked with the product in a water filled metal container.

DISPOSAL

Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.



DISCLAIMER

The technical data furnished above by the Consolidated Coatings Company is provided for information purposes only and is, to the best of our knowledge. Since application methods and conditions are beyond our control, we cannot offer a guarantee or warranty, representation, or condition, express or implied, whether arising by statute, by operation of law, or otherwise, (including merchantability or fitness for a particular purpose) with respect to this product and we assume no responsibility or liability of any kind for coverage, performance or damage (whether arising from negligence of the vendor or otherwise) resulting from the installation, operation, use or performance of this product.

7651 Vantage Way, Delta, BC, Canada, V4G 1A6

T: 604-946-7626 | F: 604-946-9609 | TF: 1-800-663-5690