CONSOLIDATED COATINGS

LOW VOC SPEED ENAMEL CLEAR SEMI-GLOSS
Product Data Sheet (Revised 11/11/21)

PRODUCT CATEGORY
Low VOC Alkyd Speed Enamel

PRODUCT CODE
1-55-0070

DESCRIPTION
Alkyd Speed Enamel Clear Semi-gloss

RECOMMENDED USE
For industrial use on all surfaces where a durable, decorative finish is necessary and speed of dry is essential. May apply on machinery, implements, hand tools, racking, shelving and many other uses.

FEATURES AND BENEFITS
• Clear coat, semi-gloss
• Fast drying
• Durable, flexible
• Good gloss and color retention

PACKAGING
3.78 can and 18.9 L Pail

PRODUCT DATA
Resin Types: Modified alkyd
Gloss: 50-60 at 60 deg.
Volume Solid: 27% ±2%
Weight solid: 38% ±2%
VOC: 356 g/L

PRACTICAL COVERAGE
9-11m^2 /liter/coat for dry film thickness at 1 mil. Actual coverage may vary depending on the type, age and texture of the substrate and application method.

DRY TIME AT 25 °C
• To touch: 30 min
• To recoat: 2 hours
• Low temperature, poor ventilation will increase these times.

GENERAL SURFACE PREPARATION
Surface to be painted must be clean, dry, and free of oil, grease, and other contamination.

CLEAN-UP SOLVENT
85-0311 Reducer

SHELF LIFE
2 years maximum-unopened

DISPOSAL
Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.