

# Light Duty Coating System for Steel

Thickness Shown In Dry Mils

72-0800 Leatherjack Alkyd Gloss Enamel (Brush, Roller or Spray)

Or

55-1000 Speed Dry Alkyd Gloss Enamel (Spray)

2-3

50-6050 Fast Dry Alkyd Primer

2-3

Surface  
Preparation  
SSPC-SP1

