

Medium Duty Coating System for Steel

55-1000 Fast Dry Alkyd Enamel (For Spray)

Or

72-0800 Leatherjacket Alkyd Enamel (Brush or Roller)


Thickness Shown In Dry Mils

2-3

2-3

50-6015 Fast Dry Phenolic Alkyd Primer

Surface
Preparation
SSPC-SP6



Steel